



AUSTINVILLE LIMESTONE CO. INC.

223 Newtown Church Road Austinville Va 24312

800-289-5963

Product Analysis

Pelletized Dolomitic Limestone

Also sold as: Pelletized LawnLime and Pro Pellets

	Minimum Guaranteed
SCREEN ANALYSIS (before pelletizing)	% Passing
10 mesh	100%
20 mesh	95%
40 mesh	90%
50 mesh	85%
60 mesh	80%
100 mesh	70%
200 Mesh	60%
CHEMICAL ANALYSIS	Content by Weight
Calcium (Ca)	21.5%
Magnesium (Mg)	11.0%
Calcium Oxide (CaO)	30.0%
Magnesium Oxide (MgO)	18.0%
Calcium Carbonate (CaCO ₃)	54.0%
Magnesium Carbonate (MgCO ₃)	38.0%
Calcium Carbonate Equivalent (CCE)	99.0%
Effective Neutralizing Power (ENP)	1768 lbs. per ton
Effective Neutralizing Value (ENV)	83.0%
Total Neutralizing Power (TNP)	99.0%
Relative Neutralizing Value (RNV)	92.0%
This product requires 1814 lbs. to equal one ton of standard liming material (with CCE of 90%).	
Agricultural Liming Materials Classification	Fine Pulverized
CAS# 16389-88-1	
Moisture Content	<1%